

INTER-MIX 5 EASY-SAND FILLER / SURFACER / REPAIR COMPOUND

An easy sanding two-part epoxy adhesive, filler and surfacer designed for cosmetic repairs on most plastics, SMC, fiberglass, steel, aluminum and other materials. Use over the top of repair compounds to fill sander marks, low spots & other imperfections.

NOTE: EASY-SAND™ was designed for cosmetic repairs on rigid and flexible parts, as an adhesive, filler and surface in thin film amounts (skim coat). Use of EASY-SAND™ in thick layers will result in less flexibility.

NOTE: Refer to "Plastic Repair Procedures" before using this product. Literature available at www.useies.com

TECHNICAL INFO

Work Time:	5 Minutes Approx.
Handling Time:	10 to 15 Minutes
Paintable:	10 Minutes
Sandable:	15 to 30 Minutes
Full Cure Strength:	6 to 8 Hours
Application Temp:	70 - 90°F (21-32°C)

CAUTION

For professional use only. Before using this or any IES product, refer to the Safety Data Sheet (SDS) and label for safe use and handling instructions.

STORAGE

Should be stored in a cool, dry location at a temperature between 50°F to 86°F (10°C to 30°C).



NEW Flexible Formula!

Easy Sand!

100% Solids, No VOC's!

0% Shrink

Quick Dry

Superior Feathering

Easy 1:1 Mix Ratio

No Special Tools Needed

PRODUCT AVAILABLE

8080	10 fl. oz. tube kit (300mL)	4 per case
8480	10 fl. oz. kit (300mL) <i>Each kit includes three #8260 static mixers</i>	4 per case
8680	6.76 fl. oz. (200 mL) <i>Each kit includes two #8260 static mixers</i>	6 per case

These suggestions and data are based on information we believe to be reliable and accurate, but no guarantee of their accuracy is made. International Epoxies & Sealers shall not be liable for any damage, loss or injury, direct or consequential arising out of the use or the inability to use the product. In every case, we urge and recommend that purchasers, before using any product in full scale production, make their own tests to determine whether the product is of satisfactory quality and suitability for their operations, and the user assumes all risk and liability whatsoever, in connection therewith.